

# C96900HT

**wieland**  
concast

Alloy C96900HT, also designated CuNi15Sn8A, is spinodal hardened (CX), reflecting properties similar to copper beryllium alloys.

Product description	Copper-nickel
Solids	Consult mill
Tubes	2" to 14" O.D.*
Rectangles	Consult mill
Standard lengths	24"***
Shape / form	semi-finished, mill stock or near-net shapes, anode, bar stock, billet / bloom, squares, hex, plate, profile or structural shape, flats / rectangular bar

\*Consult mill for wall thickness

\*\*Consult mill for other lengths

## Typical uses:

Industrial / off-road / mining / heavy equipment

- Bushings, bearings, fittings, wear plates

Oil / gas

- Bushings, bearings, fittings, components for oil refineries

Aircraft / aerospace

- Landing gear bushings and bearings



# C96900HT

Chemical composition			
Cu (%)	Sn (%)	Ni (%) <sup>1</sup>	Mn (%)
76.80	8.00	15.00	0.20

Chemical composition according to ASTM B505/B505M-23

## Mechanical properties

Tensile strength, min		Yield strength, at 0.2% offset, min		Elongation, in 4D or 2 in. or 50 mm min	Brinell hardness	Remarks
ksi	MPa	ksi	MPa	%	min BHN	
110	758	105	724	4		Heat treated Rockwell C32

Mechanical properties according to ASTM B505/B505M-23

### Key features and benefits:

- Corrosion resistance
- Wear resistance
- Impact resistance
- High strength
- Excellent bearing performance
- High stiffness ratio
- Nonmagnetic
- Exceptional lubricity
- Excellent machinability



## Wieland Concast certifications

- AS9100:2016-certified quality management system
- ISO 9001:2015-certified quality management system

Wieland Concast | 14315 State Route 113 | Wakeman, OH 44889  
P 440-965-4455 | sales@concast.com | concast.com



©2024 Wieland Concast. All rights reserved.  
Characteristics and properties of products/materials in this document are generic and provided solely for general information purposes. Any statement regarding the suitability of products/materials for certain types of applications is based on typical requirements and does not replace expert advice. Wieland disclaims all liability arising from any reliance on these documents.