

C90810

Continuous Cast • GreenAlloys™

Product Description:	High Tin Bronze
Solids:	1" to 6" O.D.
Tubes:	1" to 6" O.D.
Rectangles:	Up to 10"
Standard Lengths:	144"
Shape/Form:	semi-finished, mill stock or near-net shapes, anode, bar stock, billet/bloom, squares, hex, plate, profile or structural shape, flats/rectangular bar
Compliance:	C90810 is compliant with key legislation including (1) Federal Safe Drinking Water Act 1974 – SDWA, (2) Federal Reduction of Lead in Drinking Water Act of 2011 and (3) California AB1953

Typical Uses

Industrial bearings, gears, shafts, worm gears

Chemical Composition

Cu% ¹	Pb%	Sn%	Zn%	Fe%	P% ²	Ni% ³	Al%	S%	Sb%	Si%
Rem.	0.25	11.00- 13.00	0.30	0.15	0.15- 0.80	0.50	0.005	0.05	0.20	0.005

Chemical Composition provided by CDA

¹In determining Cu min., Cu may be calculated as Cu + Ni.

²For continuous castings, P shall be 1.5% max.

³Ni value includes Co.

Note: Cu + Sum of Named Elements, 99.4% min. Single values represent maximums.

Machinability

Copper Alloy UNS No.	Machinability Rating	Density (lb/in ³ at 68 ° F)
C90810	20	0.323

Mechanical Properties

Tensile Strength, min		Yield Strength, at 0.5% Extension Under Load, min		Elongation, in 2 in. or 50 mm min	Brinell Hardness (500 kg load)	Remarks
-----------------------	--	--	--	--------------------------------------	-----------------------------------	---------

ksi	MPa	ksi	MPa	%	typical BHN	
-----	-----	-----	-----	---	-------------	--

95