

# C92900

Cast

<b>Product Description:</b>	Leaded Nickel-Tin Bronze
<b>Solids:</b>	½" to 13" O.D.
<b>Tubes:</b>	1" to 16" O.D.
<b>Rectangles:</b>	Up to 20"
<b>Standard Lengths:</b>	144"
<b>Shape/Form:</b>	semi-finished, mill stock or near-net shapes, anode, bar stock, billet/bloom, squares, hex, plate, profile or structural shape, flats/rectangular bar

## Typical Uses

**Industrial** cams, gears, wear plates, impellers for mine water, general service bearings, pump bodies, worm gears

## Similar or Equivalent Specification

CDA	ASTM	Asarcon	SAE	AMS	Federal	Military	Other
C92900	B505 B505M	102N					

## Chemical Composition

Cu% <sup>1</sup>	Pb%	Sn%	Zn%	Fe%	P% <sup>2</sup>	Ni% <sup>3</sup>	Al%	S%	Sb%	Si%
82.00- 86.00	2.00- 3.20	9.00- 11.00	0.25	0.20	0.50	2.80- 4.00	0.005	0.05	0.25	0.005

Chemical Composition according to ASTM B505/B505M-18

<sup>1</sup>In determining Cu min., Cu may be calculated as Cu + Ni.

<sup>2</sup>For continuous castings, P shall be 1.5% max.

<sup>3</sup>Ni value includes Co.

Note: Cu + Sum of Named Elements, 99.3% min. Single values represent maximums.

## Machinability

Copper Alloy UNS No.	Machinability Rating	Density (lb/cu in at 68 °F)
C92900	40	0.320



## Mechanical Properties

C92900 continued

Tensile Strength, min		Yield Strength, at .5% Extension Under Load, min		Elongation, in 2 in. or 50 mm min	Brinell Hardness	Remarks
ksi	MPa	ksi	MPa	%	typical BHN	
45	310	25	172	8	75 (500 kg)	

Mechanical Properties according to ASTM B505/B505M-18

## Physical Properties

	US Customary	Metric
Melting Point – Liquidus	1887 °F	1031 °C
Melting Point – Solidus	1575 °F	857 °C
Incipient Melting	600 °F	316 °C
Density	0.32 lb/in <sup>3</sup> at 68 °F	8.86 gm/cm <sup>3</sup> at 20 °C
Specific Gravity	8.86	8.86
Electrical Conductivity	9% IACS at 68 °F	0.053 MegaSiemens/cm at 20 °C
Thermal Conductivity	33.6 Btu/sq ft/ft hr/°F at 68 °F	58.2 W/m at 20 °C
Coefficient of Thermal Expansion 68-392	9.5 · 10 <sup>-6</sup> per °F (68-392 °F)	16.4 · 10 <sup>-6</sup> per °C (20-200 °C)
Specific Heat Capacity	0.09 Btu/lb/°F at 68 °F	377.1 J/kg at 20 °C
Modulus of Elasticity in Tension	14000 ksi	96500 MPa

Physical Properties provided by CDA

## Fabrication Properties

Joining Technique	Suitability
Soldering	Excellent
Brazing	Good
Oxyacetylene Welding	Not Recommended
Gas Shielded Arc Welding	Not Recommended
Coated Metal Arc Welding	Not Recommended

Fabrication Properties provided by CDA

## Thermal Properties

Treatment	Temp./Time - US	Temp./Time - SI
Stress Temperature	500	260
Solution Minimum		
Solution Maximum		
Solution Time	0.0	
Solution Medium		
Precipitation Value		
Precipitation Time		
Precipitation Medium		
Annealing Minimum		
Annealing Maximum		
Annealing Time		
Hot Treatment Minimum		
Hot Treatment Maximum		

Thermal Properties provided by CDA

