

C93400

Continuous Cast

Product Description:	High-Leaded Tin Bronze
Solids:	½" to 13" O.D.
Tubes:	1" to 16" O.D.
Rectangles:	Up to 20"
Standard Lengths:	144"
Shape/Form:	semi-finished, mill stock or near-net shapes, anode, bar stock, billet/bloom, squares, hex, plate, profile or structural shape, flats/rectangular bar

Typical Uses

Fasteners washers

Industrial bearings, bushings, corrosion-resistant castings, pump impellers, slide bars, thrust bearings

Similar or Equivalent Specification

CDA	ASTM	SAE	AMS	Federal	Military	Other
C93400	B505 B505M	J461 J462		QQ-C-390, E8 QQ-B-1005, Comp 8	MIL-B-11553, Comp 8	

Chemical Composition

Cu% ¹	Pb%	Sn%	Zn%	Fe%	P%	Ni% ^{1,2}	Al%	S%	Sb%	Si%
82.00- 85.00	7.00- 9.00	7.00- 9.00	0.80	0.20	1.50	1.00	0.005	0.08	0.50	0.005

Chemical Composition according to ASTM B505/B505M-18

¹In determining Cu min., Cu may be calculated as Cu + Ni. ²Ni value includes Co.
Note: Cu + Sum of Named Elements, 99.0% min. Single values represent maximums.

Machinability

Copper Alloy UNS No.	Machinability Rating	Density (lb/in ³ at 68 ° F)
C93400	70	0.32



Mechanical Properties

Tensile Strength, min		Yield Strength, at 0.5% Extension Under Load, min		Elongation, in 2 in. or 50 mm min	Brinell Hardness (500 kg load)	Remarks
ksi	MPa	ksi	MPa	%	typical BHN	
34	234	20	138	8	60	

Mechanical Properties according to ASTM B505/B505M-18

Physical Properties

	US Customary	Metric
Density	0.32 lb/in ³ at 68 °F	8.86 gm/cm ³ at 20 °C
Specific Gravity	8.86	8.86
Electrical Conductivity	12% IACS at 68 °F	0.07 MegaSiemens/cm at 20 °C
Thermal Conductivity	33.6 Btu/sq ft/ft hr/°F at 68 °F	58.2 W/m at 20 °C
Coefficient of Thermal Expansion 68-392	10 · 10 ⁻⁶ per °F (68-392 °F)	17.3 · 10 ⁻⁶ per °C (20-200 °C)
Specific Heat Capacity	0.09 Btu/lb/°F at 68 °F	377.1 J/kg at 20 °C
Modulus of Elasticity in Tension	11000 ksi	75800 MPa

Physical Properties provided by CDA

Fabrication Properties

Technique	Suitability
Soldering	Good
Brazing*	Good
Oxyacetylene Welding	Not Recommended
Gas Shielded Arc Welding	Not Recommended
Coated Metal Arc Welding	Not Recommended
Machinability Rating	70

Fabrication Properties provided by CDA

*Since brazing is performed within the hot-short range, strain must be avoided during brazing and cooling.

Thermal Properties

Treatment	Value*	Time**
Stress Relief	500	
Solution Treatment		0

Thermal Properties provided by CDA

*Temperature is measured in Fahrenheit. **For Stress Relief, Solution Treatment and Annealing - Time is measured in hours/inch of thickness. For Precipitation Heat Treatment - Time is measured in hours.